

(19)  Canadian
Intellectual Property
Office

An Agency of
Industry Canada

Office de la Propriété,
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

(11) **CA 2 403 878** (13) **A1**

(40) 04.10.2001

(43) 04.10.2001

(12)

(21) **2 403 878**

(22) **27.03.2001**

(51) Int. Cl. 7: **C08F 8/30, C08F 8/14**

(85) **25.09.2002**

(86) **PCT/EP01/03465**

(87) **WO01/072853**

(30) **100 15 135.3 DE 29.03.2000**

(71) **BASF AKTIENGESELLSCHAFT,
D-67056, LUDWIGSHAFEN, XX (DE).**

(72)

**PFISTER, JURGEN (DE).
BUCHNER, KARL-HEINZ (DE).
WILD, JOCHEN (DE).
KRONER, MATTHIAS (DE).
PERNER, JOHANNES (DE).**

(74) **ROBIC**

(54) **PROCEDE DE MODIFICATION DE POLYMERES CONTENANT DES GROUPES D'ACIDE**

(54) **METHOD FOR MODIFYING ACID GROUP CONTAINING POLYMERS**

(57)

The invention relates to a method for modifying acid group containing polymers by reacting, at temperatures of up to 250 °C, a) polymers that contain polymerized into them at least 5 wt.-% of a monomer that contain monoethylenically unsaturated acid groups, that have a molecular weight ranging between 200 to 100.000 and that are obtainable by radical polymerization of monoethylenically unsaturated acids, optionally in the presence of another monoethylenically unsaturated monomer in an aqueous solution in the presence of at least 4 wt.-%, based on the monomers used for the polymerization, of a water-soluble sulfur composition in which the sulfur has the oxidation number +4, with b) unilaterally end-group terminated polyalkylene glycols, alkylpolyalkylene glycolamines or the mixtures thereof. The invention also relates to the mixtures of at least one of said compounds with up to 30 wt.-%, based on the mixtures, of ammonia, amines, alcohols, hydroxycarboxylic acids or aminocarboxylic acids.



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2403878 A1 2001/10/04

(21) **2 403 878**

(12) **DEMANDE DE BREVET CANADIEN
CANADIAN PATENT APPLICATION**

(13) **A1**

(86) Date de dépôt PCT/PCT Filing Date: 2001/03/27

(87) Date publication PCT/PCT Publication Date: 2001/10/04

(85) Entrée phase nationale/National Entry: 2002/09/25

(86) N° demande PCT/PCT Application No.: EP 2001/003465

(87) N° publication PCT/PCT Publication No.: 2001/072853

(30) Priorité/Priority: 2000/03/29 (100 15 135.3) DE

(51) Cl.Int.⁷/Int.Cl.⁷ C08F 8/30, C08F 8/14

(71) Demandeur/Applicant:
BASF AKTIENGESELLSCHAFT, DE

(72) Inventeurs/Inventors:
KRONER, MATTHIAS, DE;
PERNER, JOHANNES, DE;
BUCHNER, KARL-HEINZ, DE;
WILD, JOCHEN, DE;
PFISTER, JURGEN, DE

(74) Agent: ROBIC

(54) Titre : PROCEDE DE MODIFICATION DE POLYMERES CONTENANT DES GROUPES D'ACIDE
(54) Title: METHOD FOR MODIFYING ACID GROUP CONTAINING POLYMERS

(57) Abrégé/Abstract:

The invention relates to a method for modifying acid group containing polymers by reacting, at temperatures of up to 250 °C, a) polymers that contain polymerized into them at least 5 wt.-% of a monomer that contain monoethylenically unsaturated acid groups, that have a molecular weight ranging between 200 to 100.000 and that are obtainable by radical polymerization of monoethylenically unsaturated acids, optionally in the presence of another monoethylenically unsaturated monomer in an aqueous solution in the presence of at least 4 wt.-%, based on the monomers used for the polymerization, of a water-soluble sulfur composition in which the sulfur has the oxidation number +4, with b) unilaterally end-group terminated polyalkylene glycols, alkylpolyalkylene glycolamines or the mixtures thereof. The invention also relates to the mixtures of at least one of said compounds with up to 30 wt.-%, based on the mixtures, of ammonia, amines, alcohols, hydroxycarboxylic acids or aminocarboxylic acids.

Canada

<http://opic.gc.ca> · Ottawa-Hull K1A 0C9 · <http://cipo.gc.ca>

OPIC · CIPQ 191

OPIC



CIPQ

(12) NACH DEM VERTRAG ÜBER DIE INTERNATIONALE ZUSAMMENARBEIT AUF DEM GEBIET DES
PATENTWESENS (PCT) VERÖFFENTLICHTE INTERNATIONALE ANMELDUNG(19) Weltorganisation für geistiges Eigentum
Internationales Büro(43) Internationales Veröffentlichungsdatum
4. Oktober 2001 (04.10.2001)

PCT

(10) Internationale Veröffentlichungsnummer
WO 01/72853 A1(51) Internationale Patentklassifikation⁷: C08F 8/30, 8/14

(21) Internationales Aktenzeichen: PCT/EP01/03465

(22) Internationales Anmeldedatum:
27. März 2001 (27.03.2001)

(25) Einreichungssprache: Deutsch

(26) Veröffentlichungssprache: Deutsch

(30) Angaben zur Priorität:
100 15 135.3 29. März 2000 (29.03.2000) DE(71) Anmelder (für alle Bestimmungsstaaten mit Ausnahme
von US): **BASF AKTIENGESELLSCHAFT** [DE/DE];
67056 Ludwigshafen (DE).

(72) Erfinder; und

(75) Erfinder/Anmelder (nur für US): **KRONER, Matthias**
[DE/DE]; Brucknerstrasse 25, 67304 Eisenberg (DE).
PERNER, Johannes [DE/DE]; Ginsterweg 4, 67434
Neustadt (DE). **BÜCHNER, Karl-Heinz** [DE/DE]; Kirch-
feldring 14a, 68804 Altlussheim (DE). **WILD, Jochen**
[DE/DE]; St.-Martin-Strasse 22, 67152 Ruppertsberg
(DE). **PFISTER, Jürgen** [DE/DE]; St.-Klara-Kloster-Weg
62b, 67346 Speyer (DE).(74) Gemeinsamer Vertreter: **BASF AKTIENGE-
SELLSCHAFT**; 67056 Ludwigshafen (DE).(81) Bestimmungsstaaten (national): AE, AG, AL, AM, AT,
AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR,
CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK,
SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA,
ZW.(84) Bestimmungsstaaten (regional): ARIPO-Patent (GH,
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW),
eurasisches Patent (AM, AZ, BY, KG, KZ, MD, RU, TJ,
TM), europäisches Patent (AT, BE, CH, CY, DE, DK,
ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR),
OAPI-Patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML,
MR, NE, SN, TD, TG).

Veröffentlicht:

- mit internationalem Recherchenbericht
- vor Ablauf der für Änderungen der Ansprüche geltenden
Frist; Veröffentlichung wird wiederholt, falls Änderungen
eintreffen

Zur Erklärung der Zweibuchstaben-Codes, und der anderen
Abkürzungen wird auf die Erklärungen ("Guidance Notes on
Codes and Abbreviations") am Anfang jeder regulären Ausgabe
der PCT-Gazette verwiesen.

(54) Title: METHOD FOR MODIFYING ACID GROUP CONTAINING POLYMERS

(54) Bezeichnung: VERFAHREN ZUR MODIFIZIERUNG VON SÄUREGRUPPEN ENTHALTENDEN POLYMERISATEN

(57) Abstract: The invention relates to a method for modifying acid group containing polymers by reacting, at temperatures of up to 250 °C, a) polymers that contain polymerized into them at least 5 wt.-% of a monomer that contain monoethylenically unsaturated acid groups, that have a molecular weight ranging between 200 to 100.000 and that are obtainable by radical polymerization of monoethylenically unsaturated acids, optionally in the presence of another monoethylenically unsaturated monomer in an aqueous solution in the presence of at least 4 wt.-%, based on the monomers used for the polymerization, of a water-soluble sulfur composition in which the sulfur has the oxidation number +4, with b) unilaterally end-group terminated polyalkylene glycols, alkylpolyalkylene glycolamines or the mixtures thereof. The invention also relates to the mixtures of at least one of said compounds with up to 30 wt.-%, based on the mixtures, of ammonia, amines, alcohols, hydroxycarboxylic acids or aminocarboxylic acids.

(57) Zusammenfassung: Verfahren zur Modifizierung von Säuregruppen enthaltenden Polymerisaten durch Reaktion von: a) Polymeren, die mindestens 5 Gew.-% eines monoethylenisch ungesättigten Säuregruppen aufweisenden Monomeren einpolymerisiert enthalten, Molmassen von 200 bis 100.000 haben und die durch radikalische Polymerisation von monoethylenisch ungesättigten Säuren, gegebenenfalls in Gegenwart von anderen monoethylenisch ungesättigten Monomeren in wässriger Lösung in Gegenwart von mindestens 4 Gew.-%, bezogen auf die bei der Polymerisation verwendeten Monomeren, einer wasserlöslichen Schwefelverbindung erhältlich sind, in der der Schwefel die Oxidationszahl +4 hat, mit b) einseitig endgruppenverschlossenen Polyalkylenglykolen, Alkylpolyalkylenglykolaminen oder deren Mischungen, sowie Mischungen aus mindestens einer der beiden genannten Verbindungen mit bis zu 30 Gew.-%, bezogen auf die Mischungen, an Ammoniak, Aminen, Alkoholen, Hydroxycarbonsäuren oder Aminocarbonsäuren bei Temperaturen bis zu 250°C.

WO 01/72853 A1

METHOD FOR MODIFYING ACID GROUP CONTAINING POLYMERS

The present invention relates to a process for modifying polymers containing acid groups by reaction of

- (a) polymers comprising at least 5% by weight of a copolymerized monoethylenically unsaturated monomer containing acid groups and having molar masses of from 200 to 100 000, with
- (b) polyalkylene glycols which are end-capped at one end, alkylpolyalkylene glycol amines or mixtures thereof, or mixtures of at least one of the two compounds specified with up to 30% by weight, based on the mixtures, of ammonia, amines, alcohols, hydroxycarboxylic acids or aminocarboxylic acids

at up to 250°C.

US-A-5840114 discloses a cement mixture comprising a calcium salt and a copolymer containing polyalkylene oxide side chains which are bound to the main chain via an amide or imide group. Such copolymers are prepared, for example, by reacting polyacrylic acid having a molar mass of 5000 with polyalkylene glycols which are end-capped at one end and alkoxylated amines by heating to temperatures in the range of 140 - 185°C in the presence of p-toluenesulfonic acid as catalyst.

The reaction of polymers containing carboxyl groups with polyalkylene glycols which are end-capped at one end and alkylpolyalkylene glycol amines is known from US-A-5728207 and WO-A-98/31643. The effectiveness of the modified polymers obtainable in this way as dispersants for cement is still in need of improvement.

It is an object of the present invention to provide particularly effective dispersants by modification of polymers containing acid groups for cement slurries.

We have found that this object is achieved by a process for modifying polymers containing acid groups by reaction of

- (a) polymers comprising at least 5% by weight of a copolymerized monoethylenically unsaturated monomer containing acid groups and having molar masses of from 200 to 100 000 with

0050/51282

2

- (b) polyalkylene glycols which are end-capped at one end, alkylpolyalkylene glycol amines or mixtures thereof, or mixtures of at least one of the two compounds specified with up to 30% by weight, based on the mixtures, of ammonia, amines, alcohols, hydroxycarboxylic acids or aminocarboxylic acids

- at up to 250°C, when the polymers used as component (a) are ones which are obtainable by free-radical polymerization of
- 10 monoethylenically unsaturated acids in aqueous solution in the presence or absence of other monoethylenically unsaturated monomers and in the presence of at least 4% by weight, based on the monomers used in the polymerization, of a water-soluble sulfur compound in which the sulfur is in the oxidation state +4.
- 15 Such water-soluble sulfur compounds are, for example, sulfur dioxide, sulfurous acid, alkali metal, alkaline earth metal and ammonium salts of sulfurous acid or of disulfurous acid, sodium, potassium, calcium or ammonium formaldehyde sulfoxylate, dialkyl sulfites or mixtures thereof. Among these compounds, particular
- 20 preference is given to using potassium, ammonium or calcium sulfite, sodium, potassium, calcium or ammonium disulfite, sodium, potassium, calcium or ammonium hydrogensulfite or mixtures thereof.
- 25 The polymers of component (a) are obtainable by polymerization of monoethylenically unsaturated monomers containing acid groups. These monomers can be polymerized either alone, in admixture with one another or, if desired, together with other monoethylenically unsaturated monomers. Apart from the monomers containing free
- 30 acid groups, it is also possible to use the alkali metal, alkaline earth metal or ammonium salts of the monomers containing acid groups. The monomers containing acid groups can be completely neutralized or only partially neutralized, e.g. to an extent of 1 - 90%. Suitable monomers containing acid groups are,
- 35 for example, acrylic acid, methacrylic acid, maleic acid, maleic anhydride, fumaric acid, vinylsulfonic acid, allylsulfonic acid, methallylsulfonic acid, styrenesulfonic acid, acrylamido-2-methylpropanesulfonic acid, mixture of acrylic acid and methacrylic acid and mixtures of acrylic acid and methacrylic
- 40 acid [sic].

- According to the present invention, the monomers containing acid groups are polymerized in an aqueous medium at 80 - 150°C, preferably from 20 to 120°C, in the presence of water-soluble
- 45 sulfur compounds in which the sulfur is in the oxidation state +4. The polymerization can be carried out under atmospheric pressure, under superatmospheric pressure or under subatmospheric

0050/51282

3

pressure. Polymerization under superatmospheric pressure is appropriate in cases in which volatile constituents are to remain in the system, e.g. when sulfur dioxide is used as regulator or the polymerization is carried out at temperatures above the boiling point of water. The polymerization is advantageously carried out under an inert gas atmosphere. It can, for example, be carried out by metering liquid monomers such as acrylic acid or methacrylic acid without diluent, solid monomers such as maleic acid or sodium vinylsulfonate and initiators and regulators in the form of 50 - 60% strength by weight aqueous solutions into the reactor over a period of 1 - 10 hours at such a rate that the heat of polymerization can be satisfactorily removed. The concentration of the starting materials is advantageously chosen so that 30 - 70% strength by weight aqueous solutions of the polymers containing acid groups are obtained after the polymerization. The polymers may be present in neutralized or partially neutralized form. The pH of this solution is, for example, 1 - 7, preferably from 1 to 4.

Neutralization of the polymers containing acid groups can be carried out during or after the polymerization. In addition, it is possible to use monomers containing acid groups which have already been partially or completely neutralized. The sodium, potassium, calcium, magnesium or ammonium salts of the polymers containing acid groups are of particular industrial interest. In many cases, partial neutralization of the polymers containing acid groups is advantageous for storage, because partially neutralized polymers containing acid groups are more readily soluble in water and thus make it possible to prepare more highly concentrated solutions. If partially neutralized polymers containing acid groups are used, the degree of neutralization is, for example, 1 - 50 mol%, preferably 5 - 25 mol%, of the acid groups. However, polycarboxylic acids in the unneutralized form, i.e. in the acid form, can also be used as component (a). Should precipitation occur during the storage of highly concentrated aqueous polyacids, the precipitates can be redissolved by dilution with water or by storage at, for example, 40 - 100°C. Aqueous solutions of polymers containing acid groups in the acid form, the partially neutralized form or the completely neutralized form can be dried by evaporation of the water. Depending on the drying conditions, powders, granules, flakes or pellets are obtained.

As component (a), use is made, for example, of homopolymers or copolymers of acrylic acid, methacrylic acid, maleic acid, maleic anhydride, vinylsulfonic acid, acrylamidomethylpropanesulfonic acid, methallylsulfonic acid or the alkali metal or ammonium

0050/51282

4

salts of the polymers. Further examples of polymers containing acid groups are copolymers of 5 - 95% by weight of acrylic acid, methacrylic acid, maleic acid, vinylsulfonic acid, acrylamidomethylpropanesulfonic acid, methallylsulfonic acid and/or their alkali metal or ammonium salts and 95 - 5% by weight of acrylic, methacrylic or maleic esters of monohydric alcohols having 1 - 8 carbon atoms in the molecule. Polymers which are particularly preferred as component (a) are homopolymers of acrylic acid and methacrylic acid, copolymers of acrylic acid and methacrylic acid, copolymers of methacrylic acid and vinylsulfonic acid, copolymers of acrylic acid and maleic acid, copolymers of methacrylic acid and maleic acid, copolymers of acrylic acid and an ester of a monoethylenically unsaturated carboxylic acid, copolymers of methacrylic acid and an ester of a monoethylenically unsaturated carboxylic acid and the alkali metal or ammonium salts of the copolymers mentioned. The molar mass of the polymers of component (a) is 200 - 100 000, preferably from 1000 to 10 000. Particular preference is given to homopolymers of acrylic acid or methacrylic acid or copolymers of methacrylic acid and acrylic acid.


Specific examples of polymers containing acid groups (the percentages are by weight) are:

- 25 polyacrylic acid having a molecular weight of 2000,
polyacrylic acid having a molecular weight of 4000,
polyacrylic acid having a molecular weight of 8000,
polyacrylic acid having a molecular weight of 20 000,
copolymer of 70% of acrylic acid and 30% of maleic acid having a
- 30 molecular weight of 70 000,
copolymer of 50% of acrylic acid and 50% of maleic acid having a
molecular weight of 5000,
copolymer of 70% of methacrylic acid and 30% of maleic acid
having a molecular weight of 5000,
- 35 copolymer of 70% of acrylic acid and 30% of methacrylic acid
having a molecular weight of 10 000,
copolymer of 90% of acrylic acid and 10% of vinylsulfonic acid
having a molecular weight of 10 000,
copolymer of 50% of acrylic acid and 50% of methacrylic acid
- 40 having a molecular weight of 6000,
copolymer of 20% of acrylic acid and 80% of methacrylic acid
having a molecular weight of 5000,
copolymer of 80% of acrylic acid and 20% of methacrylic acid
having a molecular weight of 4000,
- 45 terpolymer of 40% of acrylic acid, 40% of methacrylic acid and
20% of maleic acid having a molecular weight of 5000.

0050/51282

5

Possible compounds of component (b) are polyalkylene glycols which are end-capped at one end, alkylpolyalkylene glycol amines and mixtures of at least one of the compounds specified with up to 30% by weight, based on the mixtures, of ammonia, amines, 5 alcohols, hydroxycarboxylic acids or aminocarboxylic acids. Polyalkylene glycols which are end-capped at one end can be represented, for example, by the formulae



where

- 15 R^1 = C₁-C₅₀-alkyl,
 R^2, R^3 = H, methyl or ethyl and
 n = 1 to 230.

The molecular weight of the alkylpolyalkylene glycols can be up 20 to 10 000; preference is given to a molecular weight of from 200 to 2000. This corresponds to up to 230, preferably from 3 to 40, alkylene oxide units per molecule.

Examples of alkylpolyalkylene glycols are:

- 25 methylpolyethylene glycol having a molecular weight of 350
 methylpolyethylene glycol having a molecular weight of 500
 methylpolyethylene glycol having a molecular weight of 750
 methylpolyethylene glycol having a molecular weight of 1000
 30 methylpolyethylene glycol having a molecular weight of 1500
 methylpolyethylene glycol having a molecular weight of 2000
 methylpolyethylene glycol having a molecular weight of 5000
 butylpolyethylene glycol having a molecular weight of 10 000
 isodecylpolyethylene glycol having a molecular weight of 1000.

35 The alkylpolyalkylene glycols may also comprise propylene oxide or butylene oxide, either alone or in combination with ethylene oxide. The combinations can be blockwise or random.

40 Examples of block polymers which are obtainable by initial addition of ethylene oxide onto one mole of methanol and subsequent addition of propylene oxide onto the ethylene oxide adduct are:

45 methylpolyalkylene glycol from 5 mole of ethylene oxide and 1 mole of propylene oxide

0050/51282

6

- methylnpolyalkylene glycol from 5 mole of ethylene oxide and
3 mole of propylene oxide
methylnpolyalkylene glycol from 5 mole of ethylene oxide and
10 mole of propylene oxide
5 methylnpolyalkylene glycol from 10 mole of ethylene oxide and
1 mole of propylene oxide
methylnpolyalkylene glycol from 10 mole of ethylene oxide and
3 mole of propylene oxide
methylnpolyalkylene glycol from 10 mole of ethylene oxide and
10 mole of propylene oxide
10 methylnpolyalkylene glycol from 20 mole of ethylene oxide and
1 mole of propylene oxide
methylnpolyalkylene glycol from 20 mole of ethylene oxide and
3 mole of propylene oxide
15 methylnpolyalkylene glycol from 20 mole of ethylene oxide and
10 mole of propylene oxide
methylnpolyalkylene glycol from 25 mole of ethylene oxide and
1 mole of propylene oxide
butyl alcohol alkoxyate from 25 mole of ethylene oxide and
20 3 mole of propylene oxide
lauryl alcohol alkoxyate from 25 mole of ethylene oxide and
10 mole of propylene oxide

It is also possible to use polytetrahydrofuran which bears, for
25 example, a C₁-C₄-alkyl group as end group at one end and has a
molar mass of from 200 to 5000.

The abovementioned alkylpolyalkylene glycols can be aminated, for
example by reaction with ammonia at elevated temperatures and
30 under superatmospheric pressure in the presence of a catalyst, to
convert the terminal OH groups into terminal amino groups. This
forms, for example, 80 - 100% of primary amino groups, from 0 to
20% by weight of secondary amino groups and from 0 to 10% by
weight of tertiary amino groups.

35

Alkylpolyalkylene glycol amines of the group (b) which are
suitable for the reaction with the polymers (a) can also be
prepared by addition of alkylpolyalkylene glycols onto the double
bond of acrylonitrile and subsequent hydrogenation of the nitrile
40 group to an amino group.

Compounds of the group (b) are, for example:

- methylnpolyethylene glycol amine from 3 ethylene oxide,
45 methylnpolyethylene glycol amine from 7 ethylene oxide,
methylnpolyethylene glycol amine from 10 ethylene oxide,
methylnpolyethylene glycol amine from 20 ethylene oxide,

0050/51282

7

- methylpolyethylene glycol amine from 30 ethylene oxide,
 methylpolyethylene glycol amine from 50 ethylene oxide,
 methylpolyethylene glycol amine from 5 ethylene oxide and
 1 propylene oxide,
 5 methylpolyethylene glycol amine from 10 ethylene oxide and
 1 propylene oxide,
 methylpolyethylene glycol amine from 10 ethylene oxide and
 3 propylene oxide,
 methylpolyethylene glycol amine from 10 ethylene oxide and
 10 10 propylene oxide,
 methylpolyethylene glycol amine from 20 ethylene oxide and
 1 propylene oxide,
 methylpolyethylene glycol amine from 20 ethylene oxide and
 3 propylene oxide,
 15 methylpolyethylene glycol amine from 20 ethylene oxide and
 10 propylene oxide,
 methylpolyethylene glycol amine from 30 ethylene oxide and
 5 propylene oxide,
 methylpolyethylene glycol amine from 40 ethylene oxide and
 20 10 propylene oxide, and
 methylpolyethylene glycol amine from 50 ethylene oxide and
 1 propylene oxide.

The mono-end-capped polyethylene glycols of the formulae I and II
 25 and the alkylpolyalkylene glycol amines can be used together with
 ammonia or amines in the preparation of the modified polymers
 containing acid groups. Suitable amines are, for example,
 alkylamines having molar masses of up to 2000 or C₃₀-dialkylamines
 having molar masses of up to 5000. Specific examples of such
 30 amines are ethylamine, butylamine, hexylamine, octylamine,
 stearylamine, tallow fatty amine and palmitylamine. It is also
 possible to use long-chain amines such as polyisobuteneamines
 having molar masses of, for example, 500, 1000 or 2000. The fatty
 amines may also be unsaturated, e.g. oleylamine. Examples of
 35 further amines are 2-methoxyethylamine, 2-methoxypropylamine,
 3-methoxypropylamine, 2-ethoxypropylamine, 3-ethoxypropylamine,
 2-(2-methoxyethoxy)propylamine, 3-(2-methoxyethoxy)propylamine.
 Further possible amines are alkoxylated alkylamines or
 alkoxylated dialkylamines, for example reaction products of 1
 40 mole of oleylamine with 20 mole of ethylene oxide or reaction
 products of 1 mole of stearylamine with 1 mole of ethylene oxide
 and 2 mole of propylene oxide or reaction products of 1 mole of
 tallow fatty amine with 1 mole of butylene oxide and 5 mole of
 ethylene oxide. Amino alcohols in combination with, for example,
 45 polyalkylene glycols which are end-capped at one end are also

0050/51282

8

suitable for the modification. Examples of such amino alcohols are ethanolamine, diethanolamine and N,N-dimethylethanolamine.

Apart from ammonia and amines, it is also possible to use
5 alcohols in admixture with polyalkylene glycols which are end-capped at one end or alkylpolyalkylene glycol amines for modifying the polymers of component (a).

Suitable alcohols are, for example, C₁-C₅₀-alcohols. Examples are
10 methanol, ethanol, isopropanol, n-propanol, butanol, hexanol, cyclohexanol, dodecanol, tridecanol, 2-ethylhexyl alcohol, hexadecanol, octadecanol, palmityl alcohol, stearyl alcohol, behenyl alcohol and tallow fatty alcohol. It is also possible to use unsaturated alcohols such as oleyl alcohol. Natural alcohols
15 or alcohols prepared by the Ziegler process or oxo alcohols can be used. The alcohols can be linear or branched.

In place of the alcohols, hydroxycarboxylic acids can also be used in the above-described mixtures. Examples are glycolic acid,
20 lactic acid, citric acid, isocitric acid, tartaric acid and malic acid. This group of compounds also includes lactones such as caprolactone.

A further group of compounds which can be used together with
25 polyalkylene glycols which are end-capped at one end and/or alkylpolyalkylene glycol amines for modifying the polymers of component (a) are amino acids. Examples of such compounds are glycine, alanine, aspartic acid, glutamic acid, glutamine, lysine, arginine, 4-aminobutyric acid, 6-aminocaproic acid,
30 11-aminoundecanoic acid and lactams such as caprolactam. Taurine is also suitable.

Examples of reactions of polymers (a) with compounds of the group (b), i.e. the polyalkylene glycols which are end-capped at one
35 end, alkylpolyalkylene glycol amines or mixtures thereof or mixtures of at least one of the two compounds specified with up to 20% by weight, based on the mixtures, of ammonia, amines, alcohols, hydroxycarboxylic acids or aminocarboxylic acids, are:

40 15% by weight of polyacrylic acid, 80% by weight of methylpolyethylene glycol and 5% by weight of methylpolyethylene glycol amine

30% by weight of polyacrylic acid, 65% by weight of
45 methylpolyethylene glycol and 5% by weight of methylpolyethylene glycol amine

0050/51282

9

40% by weight of polyacrylic acid, 55% by weight of methylpolyethylene glycol and 5% by weight of methylpolyethylene glycol amine

5 10% by weight of polyacrylic acid, 70% by weight of methylpolyethylene glycol and 20% by weight of methylpolyethylene glycol amine

15% by weight of polymethacrylic acid, 80% by weight of methylpolyethylene glycol and 5% by weight of methylpolyethylene glycol amine

15% by weight of copolymer of acrylic acid and methacrylic acid, 80% by weight of methylpolyethylene glycol and 5% by weight of methylpolyethylene glycol amine

15% by weight of copolymer of acrylic acid and maleic acid, 80% by weight of methylpolyethylene glycol and 5% by weight of methylpolyethylene glycol amine

20 10% by weight of polyacrylic acid and 90% by weight of methylpolyethylene glycol

15% by weight of copolymer of methacrylic acid and maleic acid, 80% by weight of methylpolyethylene glycol and 5% by weight of methylpolyethylene glycol amine

20% by weight of polyacrylic acid and 80% by weight of methylpolyethylene glycol

30 30% by weight of polyacrylic acid and 70% by weight of methylpolyethylene glycol

40% by weight of polyacrylic acid and 60% by weight of methylpolyethylene glycol.

35 It is also possible to use 2 or more alkylpolyalkylene glycols of group (b) for the reaction with one or more of the polycarboxylic acids of group (a), for example:

40 10% by weight of polyacrylic acid, 45% by weight of methylpolyethylene glycol having a molar mass of 500 and 45% by weight of methylpolyethylene glycol having a molar mass of 2000

45

0050/51282

10

20% by weight of polymethacrylic acid, 30% by weight of methylpolyethylene glycol having a molar mass of 500 and 50% by weight of methylpolyethylene glycol having a molar mass of 1000

5 30% by weight of polyacrylic acid, 20% by weight of methylpolyethylene glycol having a molar mass of 300 and 50% by weight of methylpolyethylene glycol having a molar mass of 4000

40% by weight of polyacrylic acid, 10% by weight of methylpolyethylene glycol having a molar mass of 500 and 50% by weight of methylpolyethylene glycol having a molar mass of 2000

20% by weight of polymethacrylic acid, 30% by weight of methylpolyethylene glycol having a molar mass of 1000 and 50% by weight of methylpolyethylene glycol having a molar mass of 5000

20% by weight of copolymer of acrylic acid and methacrylic acid in a weight ratio of 1:1, 30% by weight of methylpolyethylene glycol having a molar mass of 500 and 50% by weight of methylpolyethylene glycol having a molar mass of 1000

20% by weight of copolymer of acrylic acid and methacrylic acid in a weight ratio of 1:9, 60% by weight of methylpolyethylene glycol having a molar mass of 500 and 20% by weight of methylpolyethylene glycol having a molar mass of 1000

20% by weight of copolymer of acrylic acid and maleic acid in a weight ratio of 3:7, 50% by weight of methylpolyethylene glycol having a molar mass of 500 and 30% by weight of methylpolyethylene glycol having a molar mass of 2000

10% by weight of polyacrylic acid, 10% by weight of copolymer of acrylic acid and methacrylic acid in a weight ratio of 3:7, 50% by weight of methylpolyethylene glycol having a molar mass of 500 and 30% by weight of methylpolyethylene glycol having a molar mass of 2000

20% by weight of polymethacrylic acid, 10% by weight of copolymer of acrylic acid and methacrylic acid in a weight ratio of 7:3, 30% by weight of methylpolyethylene glycol having a molar mass of 500 and 50% by weight of methylpolyethylene glycol having a molar mass of 2000

10% by weight of polyacrylic acid and 90% by weight of methylpolyethylene glycol amine

0050/51282

11

20% by weight of polyacrylic acid and 80% by weight of methylpolyethylene glycol amine

30% by weight of polyacrylic acid and 70% by weight of
5 methylpolyethylene glycol amine

40% by weight of polyacrylic acid and 60% by weight of methylpolyethylene glycol amine

10 20% by weight of polyacrylic acid, 74% by weight of methylpolyethylene glycol, 5% by weight of methylpolyethylene glycol amine and 1% by weight of ammonia

20% by weight of polyacrylic acid, 75% by weight of
15 methylpolyethylene glycol, 5% by weight of 2-methoxyethylamine

20% by weight of polyacrylic acid, 75% by weight of methylpolyethylene glycol, 5% by weight of 2-methoxypropylamine

20 15% by weight of polyacrylic acid, 80% by weight of methylpolyethylene glycol, 5% by weight of 2-methoxypropylamine

15% by weight of polyacrylic acid, 80% by weight of methylpolyethylene glycol, 5% by weight of 3-methoxypropylamine
25

20% by weight of polyacrylic acid, 70% by weight of methylpolyethylene glycol, 10% by weight of 3-(2-methoxyethoxy)propylamine and

30 20% by weight of polyacrylic acid, 70% by weight of methylpolyethylene glycol, 10% by weight of 2-(2-methoxyethoxy)propylamine

The molar masses of the polymers (a) and the polyalkylene glycols
35 which are end-capped at one end or alkylpolyalkylene glycol amines (b) mentioned above by way of example are in the range indicated above for the compounds (a) and (b).

The reaction of the components (a) and (b) can be carried out in the presence or absence of catalysts. Catalysts which may be used
40 are, for example, sulfuric acid, p-toluenesulfonic acid, benzenesulfonic acid, methanesulfonic acid, phosphoric acid, phosphorous acid or hydrochloric acid. If an acid acting as catalyst is used in the reaction, it is used in an amount of up to 10% by weight, preferably up to 5% by weight, based on the
45 components (a) and (b).

0050/51282

12

The weight ratio in which the compounds of groups (a) and (b) are reacted can be from 99:1 to 1:99. The components (a) and (b) are preferably reacted in a weight ratio of from 50:50 to 5:95, particularly preferably from 30:70 to 10:90.

5

The reaction is carried out, for example, by admixing the aqueous solutions of the component (a) with, if desired, an acid acting as catalyst and with a compound of the component (b) and distilling off the water. The water is usually distilled from the
10 mixture under atmospheric pressure, but can also be carried out under reduced pressure. It is often advantageous to pass a stream of gas through the reaction mixture during the distillation in order to remove the water and other volatile constituents more quickly. As stream of gas, it is possible to use air, nitrogen or
15 steam. However, it is also possible for the water to be removed under reduced pressure and for a stream of gas to be passed through the reaction mixture in addition. To distill the water from the reaction mixture, energy has to be supplied to the mixture. Suitable apparatuses for this purpose are heatable
20 stirred vessels, stirred vessels with external heat exchangers, stirred vessels with internal heat exchangers, thin film evaporators, kneaders and extruders. The water which vaporizes is taken from the reaction medium via a vapor line and is condensed in a heat exchanger. It contains only small amounts of organic
25 constituents and can be disposed of via a water treatment plant.

Subsequent to or simultaneously with the removal of water from the reaction mixture, a condensation reaction between the compounds of the components (a) and (b) occurs. The water formed
30 in this condensation reaction is likewise removed from the reaction medium. The modification of the compound of component (a) is carried out at, for example, from 100 to 250°C. This temperature depends on the reaction apparatus and the residence time. If, for example, the condensation is carried out in a
35 continuously operated extruder or thin film evaporator in which the residence time is only a few seconds or minutes, it is advantageous to employ temperatures in the range from 150 to 250°C. In batchwise operation in stirred vessels or kneaders, the residence time required is, for example, 1-15 hours and the
40 condensation is usually carried out in the temperature range of 100 - 200°C.

In one process variant, the polymers (a) containing acid groups can be dewatered first and the resulting powder or granulated
45 material can be condensed with at least one compound of component (b).

0050/51282

13

After the condensation, the reaction mixture is cooled and, if appropriate, dissolved in water. Aqueous solutions of the reaction mixture can be prepared, for example, by adding water to the reaction mixture still at 50 - 150°C while stirring or by stirring the liquid reaction mixture at 50 - 150°C into water. It is usual to employ such an amount of water that a 20-95% strength by weight, preferably 30-50% strength by weight, aqueous solution of the modification product is obtained. Simultaneously with or subsequent to the dissolution of the condensation product, neutralization of the remaining acid groups can be carried out if desired. As neutralization agents, use is made of alkali metal or alkaline earth metal oxides or hydroxides in solid form or in the form of 10-50% strength aqueous solutions or slurries in water. Examples of suitable bases are lithium hydroxide, sodium hydroxide, potassium hydroxide, calcium oxide, calcium hydroxide, magnesium oxide, magnesium hydroxide, aluminum oxide and aluminum hydroxide. Depending on the degree of neutralization, the aqueous solutions of the modified polycarboxylic acids can have pH values in the range from 1 to 7.

The reaction mixture can also remain undiluted after the condensation. On cooling to below 60°C, it crystallizes to a waxy mass which can readily be melted again. This results in varying possibilities for transport. For example, the reaction mixture can be packed in drums from which the condensation product can be melted again. It can also be transported and stored in the molten state at above 60°C, preferably at from 80 to 120°C. Heatable and thermally insulated tankers are suitable for this. The melt can be stored in heated storage containers at from 80 to 120°C.

However, it is also possible to prepare a 60 - 90% strength aqueous solution and to handle this. The viscosities of such solutions are, for example, from 1000 to 100 000 mPas. Addition of from 1 to 40% by weight of water to the melt can reduce the softening temperature. Thus, a condensation product without water melts, for example, at 50°C, with 5% of water at 45°C and with 10% of water at only 30°C. Addition of 20 - 40% by weight of water allows the solutions to be readily handled at 20 - 40°C. This plasticizing action of the water can be advantageous for handling of the melt, since it can reduce the storage temperature and the melt viscosity is also lowered.

The water-free melt can also be mixed with inert powders so as to obtain free-flowing granular material. Inert powders which can be used are, for example, kieselguhr, silica gel, amorphous silicic acid and/or amorphous silicon dioxide.

0050/51282

14

The aqueous polymer solutions of the modified polymers containing acid groups which can be obtained in this way are used, for example, as dispersants for cement.

- 5 The percentages given in the examples are by weight. The K value of the polymers was determined by the method of H. Fikentscher, Cellulose-Chemie, Volume 13, 58-64 and 71 - 74 (1932), in aqueous solution at a pH of 7, a temperature of 25°C and a polymer concentration of the sodium salt of the polymers of 1% by weight.

10

Examples

Preparation of aqueous polycarboxylic acid solutions

15 Polycarboxylic acid 1

- In a 3 liter polymerization reactor, 500 g of water were heated to 100°C while passing nitrogen through it. As soon as the water boiled, 1200 g of acrylic acid, 300 g of 40% strength aqueous sodium bisulfite solution and 350 g of 10% strength aqueous sodium peroxodisulfate solution were metered in simultaneously over a period of 6 hours. After the addition was complete, the reaction mixture was subjected to post-polymerization for a further one hour and 200 g of 50% strength aqueous sodium hydroxide were then added to give an aqueous solution of partially neutralized polyacrylic acid. The molecular weight of the polyacrylic acid was 4000. The solids content of the polymer solution was adjusted to 50% by dilution with water.

30 Polycarboxylic acid 2

- In a 4 liter reactor, 1600 g of water were heated to 100°C while passing nitrogen through it. As soon as the water started to boil, 570 g of acrylic acid, 680 g of methacrylic acid, 250 g of 40% strength sodium bisulfite solution and 500 g of 10% strength sodium peroxodisulfate solution were metered in simultaneously over a period of 7 hours. After the addition was complete, the reaction mixture was polymerized for another one hour by heating at 100°C. The polycarboxylic acid had a molar mass of 5500 and a K value of 31. The solids content of the aqueous polymer solution was 38%.

Example 1

- 45 250 g of the 50% strength aqueous polycarboxylic acid 1 having a molecular weight of 4000, 6 g of concentrated sulfuric acid, 50 g of methylpolyethylene glycol amine having a molecular weight of

0050/51282

15

500 and 550 g of methylpolyethylene glycol having a molar mass of 1000 were placed in a 2 liter reactor provided with an anchor stirrer. The water was subsequently distilled off at 50 mbar. The temperature was then increased to 180°C and condensation was carried out for 5 hours under reduced pressure. After condensation was complete, the reaction mixture was cooled to 90°C and 900 g of water and 5 g of 50% strength aqueous sodium hydroxide were added. This gave a 40% strength aqueous polymer solution. The molecular weight M_w of the modified polyacrylic acid was 23 000. The modified polyacrylic acid had a K value of 23.

Example 2

250 g of the polycarboxylic acid 1 were admixed with 20 g of 25% strength aqueous ammonia solution, 550 g of methylpolyethylene glycol having a molar mass of 1000 and 6 g of concentrated sulfuric acid. The mixture was subsequently condensed as described in Example 1, and water and sodium hydroxide were then added to give a 40% strength aqueous solution of the modified polyacrylic acid having a molar mass of 25 000. The K value of the modified polyacrylic acid was 24.

Example 3

Example 2 was repeated except that the condensation was carried out in the absence of ammonia. A 40% strength aqueous polymer solution was obtained. The molecular weight of the modified polyacrylic acid was 20 000, and the K value was 23.

30 Example 4

Example 2 was repeated except that 50 g of n-butylamine were used in place of the ammonia. The modified polycarboxylic acid 1 had a molar mass of 20 000 and a K value of 24.

35

Example 5

In a 2 liter reactor, 300 g of the polycarboxylic acid 2 were admixed with 600 g of methylpolyethylene glycol having a molar mass of 1000 and 10 g of concentrated sulfuric acid, the mixture was heated to 160°C while distilling off water and condensed for 4 hours at this temperature. After cooling and dilution to a solids content of 40%, the reaction mixture was partially neutralized by addition of 10 g of 50% strength aqueous sodium hydroxide. The modified polyacrylic acid had a molar mass of 28 000 and a K value of 32.

0050/51282

16

Example 6

Example 5 was repeated except that 400 g of methylpolyethylene glycol amine having a molar mass of 500 was used in place of 5 methylpolyethylene glycol. The modified polycarboxylic acid had a molar mass of 22 000 and a K value of 27.

10

15

20

25

30

35

40

45

005/51282

17


We claim:

1. A process for modifying polymers containing acid groups by
5 reaction of
 - (a) polymers comprising at least 5% by weight of a
copolymerized monoethylenically unsaturated monomer
containing acid groups and having molar masses of from
10 200 to 100 000 with
 - (b) polyalkylene glycols which are end-capped at one end,
alkylpolyalkylene glycol amines or mixtures thereof, or
mixtures of at least one of the two compounds specified
15 with up to 30% by weight, based on the mixtures, of
ammonia, amines, alcohols, hydroxycarboxylic acids or
aminocarboxylic acidsat up to 250°C, wherein the polymers used as component (a)
20 are ones which are obtainable by free-radical polymerization
of monoethylenically unsaturated acids in aqueous solution in
the presence or absence of other monoethylenically
unsaturated monomers and in the presence of at least 4% by
weight, based on the monomers used in the polymerization, of
25 a water-soluble sulfur compound in which the sulfur is in the
oxidation state +4.
2. A process as claimed in claim 1, wherein the water-soluble
sulfur compound used is sulfur dioxide, sulfurous acid, an
30 alkali metal, alkaline earth metal or ammonium salt of
sulfurous acid or of disulfurous acid, a sodium, potassium or
ammonium formaldehyde sulfoxylate, a dialkyl sulfite or a
mixture thereof.
- 35 3. A process as claimed in claim 1 or 2, wherein the
water-soluble sulfur compound used is sodium, potassium or
ammonium sulfite, sodium, potassium, calcium or ammonium
disulfite, sodium, potassium, calcium or ammonium
hydrogensulfite or a mixture thereof.
40
4. A process as claimed in any of claims 1 to 3, wherein the
water-soluble sulfur compound is used in an amount of from 4
to 15% by weight, based on the monomers used in the
polymerization.
45

0050/51282

18


5. A process as claimed in any of claims 1 to 4, wherein the compounds used in component (a) are homopolymers or copolymers of acrylic acid, methacrylic acid, maleic acid, maleic anhydride, vinylsulfonic acid, acrylamidomethyl-
 5 propanesulfonic acid, methallylsulfonic acid or alkali metal or ammonium salts of the monomers specified.
6. A process as claimed in any of claims 1 to 5, wherein the component (a) used comprises copolymers of from 5 to 95% by
 10 weight of acrylic acid, methacrylic acid, maleic acid, maleic anhydride, vinylsulfonic acid, acrylamidomethylpropane-sulfonic acid, methallylsulfonic acid and/or their alkali metal or ammonium salts and from 95 to 5% by weight of acrylic, methacrylic or maleic esters of monohydric alcohols
 15 having 1 to 8 carbon atoms in the molecule.
7. A process as claimed in any of claims 1 to 6, wherein the component (a) used comprises homopolymers of acrylic acid, homopolymers of methacrylic acid, copolymers of acrylic acid and methacrylic acid, copolymers of methacrylic acid and vinylsulfonic acid, copolymers of acrylic acid and maleic acid, copolymers of methacrylic acid and maleic acid, copolymers of acrylic acid and an ester of a
 20 monoethylenically unsaturated carboxylic acid, copolymers of methacrylic acid and an ester of a monoethylenically unsaturated carboxylic acid and/or alkali metal or ammonium salts of the copolymers specified.
8. A process as claimed in any of claims 1 to 7, wherein the
 30 molar mass of the polymers of component (a) is from 1000 to 10 000.
9. A process as claimed in any of claims 1 to 8, wherein the component (a) used comprises homopolymers of acrylic acid or
 35 methacrylic acid or copolymers of methacrylic acid and acrylic acid.
10. A process as claimed in any of claims 1 to 9, wherein the component (b) used comprises polyalkylene glycols which are
 40 end-capped at one end and have the formula



45 where

$R^1 = C_1-C_{50}\text{-alkyl},$

0050/51282



19

R^2, R^3 = H, methyl or ethyl and
 n = 1 to 100.

11. A process as claimed in any of claims 1 to 10, wherein the compounds used in component (b) are methylpolyethylene glycols or methylpolyalkylene glycols comprising ethylene oxide and propylene oxide, in each case having molar masses of from 200 to 10 000.

10

15

20

25

30

35

40

45

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)